

**SIR-300** 

**RESINTECH SIR-300** is a macroporous weak acid cation exchange resin based on the iminodiacetate acid functional group, which has chelating properties for heavy metal ions even against high concentrations of calcium. It is intended for use in polishing heavy metal ions from near neutral industrial wastes and process streams, and recovery of precious metals. *RESINTECH SIR-300* is supplied in the sodium form as moist, tough, uniform spherical beads.

### **FEATURES & BENEFITS**

- ABLE TO CHELATE HEAVY METALS IN METAL FINISHING RINSES
   Extremely high selectivity for metals in slightly acid waters makes resin ideal for treatment prior to discharge,
   or in front of other resins used in recycle, recovery loops.
- **ABLE TO CHELATE HEAVY METAL IONS IN HIGH CALCIUM CONCENTRATIONS** High capacity for removing traces of heavy metals from wastewaters that have been treated by conventional hydroxide precipitation.
- HIGHLY UNIFORM PARTICLE SIZE

16 to 50 mesh range; giving a LOW PRESSURE DROP while maintaining EXCELLENT KINETICS.

### SUPERIOR PHYSICAL STABILITY

95% sphericity combined with a macroporous polymer structure, high crush strength and uniform particle size distribution gives greater resistance to bead breakage and osmotic shock.

## HYDRAULIC PROPERTIES

**PRESSURE DROP** 



#### **Backwash Expansion** 100 80 00 Percent Expansion 60°F 60 **80**° 40 00°F 20 0 1 3 5 6 0 Flow Rate, gpm/sq.ft.

#### BACKWASH

After each cycle the resin bed should be backwashed at a rate that expands the bed 50 to 75 percent. This will remove any foreign matter and reclassify the bed.



The graph above shows the expected pressure loss per foot of bed

depth as a function of flow rate at various water temperatures.

# **RESINTECH® SIR-300**

### **TYPICAL PROPERTIES**

Polymer Structure Functional Group Ionic Form, as shipped Physical Form Screen Size Distribution +16 mesh (U.S. Std) - 50 mesh " " pH Range Water Retention Sodium Form Solubility Approximate Shipping Weight Sodium Form Swelling H- to Na- Form

Total Capacity Sphericity Macroporous Styrene with DVB R-CH<sub>2</sub>-N(COOH)<sub>2</sub> Sodium Spherical Beads 16 to 50 < 5 percent < 1 percent 1.5 to 14

55 to 60 percent Insoluble

43 lbs./cu. ft. 20 percent

> 1.1 meq/mL Na form
> 95 percent

### SUGGESTED OPERATING CONDITIONS

170<sup>0</sup>F

Maximum Temperature Salt form Hydrogen form Maximum Free Chlorine Minimum Bed Depth Backwash Rate Acid Regenerant Conc. Regenerant Flow Rate Regenerant Contact Time Regenerant Level

Displacement Rinse Rate Displacement Rinse Volume Fast Rinse Rate Fast Rinse Volume Caustic Neutralization Conc. Caustic Solution Flow Rate Caustic Contact Time Caustic Dose Level Displacement Rinse Rate Displacement Rinse Volume Fast Rinse Rate Fast Rinse Volume Service Flow Rate 140<sup>0</sup>F NONE 36 inches 50 to 75 % Bed Expansion 4 to 10% 0.25 to .5 gpm/cu. ft. At least 30 Minutes 8.7 (HCl) or 12.5 (H<sub>2</sub>SO<sub>4</sub>) lbs/cu. ft. Same as Regenerant Flow Rate 10 to 20 gallons/cu. ft. Same as Service Flow Rate 35 to 60 gals./cu. ft. 4 to 10% 0.25 to .5 gpm/cu. ft. At least 30 Minutes 2.5 to 6.0 pounds/cu. ft. Same as Regenerant Flow Rate 10 to 20 gallons/cu. ft. Same as Service Flow Rate 35 to 60 gals./cu. ft. 1 to 2 gpm/cu. ft.

### **OPERATING CAPACITY**

The relative affinity of ResinTech SIR-300 for heavy metals in near neutral solutions is in accordance with the following sequence.

H<sup>+1</sup>>>Cu<sup>+2</sup>>V<sup>+2</sup>>>(UO2)<sup>+2</sup>>Pb<sup>+2</sup>>Ni<sup>+2</sup>>Zn<sup>+2</sup>>Co<sup>+2</sup>>Cd<sup>+2</sup>>Fe<sup>+2</sup>>Be<sup>+2</sup>>Mn<sup>+2</sup>>Mg+2Ca<sup>+2</sup>>Sr<sup>+2</sup>>Ba<sup>+2</sup>>>Na<sup>+1</sup>

High concentrations of chlorides or sulfates, or the presence of cheating or complexing agents can alter this sequence and likewise will affect the operating capacity.

#### **HIGH CHLORIDE SOLUTIONS**

Cu<sup>+2</sup>>Ni<sup>+2</sup>>Co<sup>+2</sup>>Zn<sup>+2</sup>>Cd<sup>+2</sup>>Fe<sup>+2</sup>

#### HIGH SULFATE SOLUTIONS

Cu+2>Ni+2>Cd+2>Zn+2>Co+2>Fe+2

*RESINTECH SIR-300* has similar chelating characteristics to EDTA and NTA. Therefore it is less effective when these agents are present.

For each particular metal cation there is a critical pH at which ResinTech SIR-300 has optimum selectivity. For most metals this pH is approximately 4.0. As the pH decreases, so does the selectivity. At a pH of approximately 1.5 *RESINTECH SIR-300* loses its ability to remove most metals. The minimum pH values for removal of some common metal ions are as follows:

Vanganese	4.0
ron	3.0
Zinc, Cobalt	2.7
Vickel	2.5
Copper	1.5

As the pH increases, selectivity also decreases. At a pH of 9.0 selectivity for most metals is about 10% of the selectivity at optimum pH. Above a pH of 9.0 many metals form anionic complexes and are no longer present in a form that can be removed by *ResINTECH SIR-300*.

*RESINTECH SIR-300*, like other chelating resins, has very slow kinetics. Optimum capacity is obtained when the service flow rate is limited to 0.5 to 1.0 gpm/cu. ft.. Where extremely low leakage of metals is required, two columns of *RESINTECH SIR-300* should be operated in series . The primary column can be fully exhausted, allowing the polishing column to protect against leakage. After regeneration, the order of the columns is reversed with the freshly regenerated column used as the polisher.

*ResinTech SIR-300* is useful in numerous applications including Waste Treatment, Chemical Processing and Resource Recovery.

*RESINTECH SIR-300* can be used to selectively remove heavy metal multivalent ions from a variety of industrial effluents such as oil refineries, plating shops, mine drainage, battery manufacturing, and cooling towers. Consult your ResinTech technical representative for specific applications.



Industry Leader in RO Expertise and Membrane Applications since 1983™

\*CAUTION:DO NOT MIX ION EXCHANGE RESIN WITH STRONG OXIDIZING AGENTS. Nitric acid and other strong oxidizing agents can cause explosive reactions when mixed with organic materials, such as ion exchange resins.

Material Safety Data Sheets (MSDS) are available for all ResinTech Inc.products. To obtain a copy,contact your local ResinTech sales representative or our corporate headquarters. They contain important health and safety information. That information may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

**RESINTECH** is a registered trademark  $\mathbb{R}$  of RESINTECH INC